

Stereax® P180 – Extended Temperature Range Solid State Battery: -40° to + 150°C

Features

- ▲ Operates in Commercial, Industrial, Extended and Automotive Temperature Ranges
- ▲ Thin Form factor
- ▲ All Solid-State Construction
- ▲ Fast Charge
- ▲ High Current Pulses
- ▲ High Energy Density per Footprint
- ▲ Thousands of Cycles
- ▲ Low Self-discharge
- ▲ No Free Lithium
- ▲ Eco-friendly




Stereax P180 solid state batteries deposited on 6" wafer

Physical Properties

Active Area:	10 mm x 10 mm
Thickness ^a :	1.0 mm
Mass:	620 mg
Operating temperature:	-40°C to +150°C

Electrical Properties at +150 °C

Output Voltage (nominal):	3.4 V
Capacity (nominal):	180 µAh
Charging Source:	3.8 V
Charging time to 90%:	<1 minute
Charge/discharge cycles ^b :	up to 4,000
Peak current:	18 mA



Encapsulation (1.4cmx1.4cm)	Cathode (1cmx1cm)
Anode Current Collector (1cmx1cm)	Cathode Current Collector (1cmx1cm)
Anode (1cmx1cm)	Substrate
Electrolyte (1.2cmx1.2cm)	

Stereax P180 expanded construction diagram

a: Thickness value includes substrate (650 µm). Thinner substrates are available.
 b: 5% DoD

General Description

The Stereax P180 is a unique solid state battery that can operate and be stored in the extended temperature range -40°C to +150°C.

The size and performance of the Stereax P180 solid state battery make it ideal to power autonomous sensor devices in the Internet of Things. In particular, its performance at high temperature, up to +150°C, enable the deployment of end nodes situated near hot machinery in Industry 4.0 or engines and exhausts in smart cars. At low temperature, to -40°C, such end nodes may be deployed to monitor infrastructure such as pipelines or bridges.

The Stereax technology platform is developed by Ilika who licenses its IP portfolio and know-how based on deposition processes and materials to systems and components OEMs and manufacturers. This format allows Ilika to respond to partners' requirements more efficiently than manufacturing standardised product lines, for an optimal outcome and greater flexibility in terms of shape, capacity, life cycle...

Applications

- ▲ Autonomous Sensor Devices
- ▲ Industrial
- ▲ Automotive
- ▲ Aerospace
- ▲ Infrastructure monitoring

Specifications

Temperature	Parameter	Test conditions	Value	Unit
-40°C	Capacity	C/60	160	μAh
	Operating Voltage		2.9 – 4.1	V
	Max Continuous Current	C/30	6	μA
	Standard Discharge Current	C/60	3	μA
	Internal Resistance	Charge Cycle 1, 100% SoC	7500	Ω
Temperature	Parameter	Test conditions	Value	Unit
+25°C	Capacity	1C	180	μAh
	Operating Voltage		3 - 4	V
	Max Continuous Current	10C	1.8	mA
	Standard Discharge Current	1C	180	μA
	Cycle life	5% DoD; to 80% of rated capacity; 1C	5000	Cycles
		100% DoD to 80% of rated capacity; 1C	900	Cycles
	Internal Resistance	Charge Cycle 1, 100% SoC	120	Ω
Pulse Current	0.5 ms, every second	3.6	mA	
Temperature	Parameter	Test conditions	Value	Unit
+150°C	Capacity	1C	180	μAh
	Operating Voltage		3 – 3.8	V
	Max Continuous Current	50C	9	mA
	Standard Discharge Current	1C	180	μA
	Cycle life	5% DoD; to 80% of rated capacity; 1C	4000	Cycles
		100% DoD to 80% of rated capacity; 1C	200	Cycles
	Internal Resistance	Charge Cycle 1, 100% SoC	15	Ω
Pulse Current	0.5 ms, every second	18	mA	

Note: All specifications contained within this document are subject to change without notice.

Disclaimer of Warranties; As Is

The information provided in this data sheet is provided "As Is" and Ilika Technologies disclaims all representations or warranties of any kind, express or implied, relating to this data sheet and the Ilika Stereax product described herein, including without limitation, the implied warranties of merchantability, fitness for a particular purpose, non-infringement, title, or any warranties arising out of course of dealing, course of performance, or usage of trade. Ilika Stereax products are not approved for use in life critical applications. Users shall confirm suitability of the Ilika Stereax product in any products or applications in which the Ilika Stereax product is adopted for use and are solely responsible for all legal, regulatory, and safety-related requirements concerning their products and applications and any use of the Ilika Stereax product described herein in any such product or applications.

Ilika, the Ilika logo and Stereax are trademark of Ilika technologies. All rights reserved

accelerated materials innovation

Ilika Technologies Ltd, Kenneth Dibben House, Enterprise Road, University of Southampton Science Park, Chilworth, Southampton, SO16 7NS, UK

Tel: +44 (0)23 8011 1400 | Fax: +44 (0)23 8011 1401 | Email info@ilika.com | www.ilika.com | [in /ilika-plc](https://www.linkedin.com/company/ilika) | [@ilikaplc](https://twitter.com/ilikaplc)

Copyright 2018. All right reserved.

P180 SPECIFICATION V3.4 - ENGLISH